



INSTRUKCE PRO SUSENI INFRA - LAMPAMI (I.R.)

	Kód	Název	Odvětrání	Doba sušení	Vzdálenost	Max. teplota
			min.	min.	cm	°C
T M E L Y	04461	POLYDUR CART		6	60-80	70
	04462	POLYDUR FAST		6	60-80	70
	04380	POLYDUR ZINC	2	7	60-80	70
	05331	MULTILIGHT	2	7	70	70
P L N I Č E	04109	GREEN TI FILLER	0-5*	10-15	70	70
	04004	GREEN TI FILLER GREY	0-5*	10-15	70	70
	MAC71	MACROFAN HS COLOR HIGH FILLER	5-6	10-12	70-80	70
	04706-710	MACROFAN HS HIGH FILLER	5-6	10-12	70-80	70
	MAC75	MACROFAN HS COLOR RAPID FILLER	5-6	8-10	60-80	70
	04806-810	MACROFAN HS RAPID FILLER	5-6	8-10	60-80	70
	MAC85	MACROFAN HS COLOR ISOSEALER	0-6*	10-15	60-80	70
	04804	MACROFAN HS ISOSEALER	0-5*	10-15	60-80	70
KRYCÍ LAK	MAC 4	MACROFAN ULTRA HS	5-6	10-12	60-80	80
B E Z B L A A R K V Ý	MC420	MACROFAN UHS CLEARCOAT	7-8	15-20	60-80	80
	MC422	MACROFAN ELITE UHS CLEARCOAT	5	15-20	60-80	80
	HF950	HYDROFAN 2K CLEARCOAT	10-15	20-25	60-80	80

* doporučeno 5 min.